



# OxyVinyls<sup>®</sup> 225P



## General Description

Type: Polyvinyl Chloride Homopolymer  
Polymerization Process: Suspension  
Appearance: White, free flowing powder

## Features and Uses:

OxyVinyls<sup>®</sup>225P resin is often converted into a wide range of pipe sizes and types, which meet the most stringent standards for water supply and distribution. Its medium molecular weight provides excellent processing characteristics in both single and multi-screw extruders. Typical Applications include irrigation, foam core, potable water, DWV/sewer pipe, electrical conduit and rigid profiles.

Resin Properties	Typical Value	Specification Range	Test Method
Inherent Viscosity (dl/g)	0.900	0.880 – 0.920	OxyVinyls 1386
Relative Viscosity	2.16	2.12 – 2.19	Correlation
K Value	65	64 – 65	Correlation
Volatiles (%)	0.07	0.24 Max.	OxyVinyls 1242
Malvern Particle Size			
% Retained on 40 mesh	0.1	0.5 Max.	OxyVinyls 1505
% Retained on 60 mesh	3.2	7.0 Max.	OxyVinyls 1502
% Retained on 200 mesh	8.0	15.0 Max.	
% Retained on Pan	1.1	5.0 Max.	
Residual Monomer (ppm)	0.15	3.2 Max.	OxyVinyls 1005
Apparent Bulk Density (g/cc)	0.543	0.515 – 0.575	OxyVinyls 1501
ASTM Cell Classification	GP4-16040		ASTM D 1755
CAS Number	9002-86-2		

## OxyVinyls, LP

Occidental Tower  
5005 LBJ Freeway  
Dallas, Texas 75244  
877-699-8465

Pasadena Plant  
January 2012

**Important:** The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guarantee, express or implied, is made regarding performance, stability or otherwise. This information is not intended to be all-inclusive as the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any Federal, State, or local laws.