

## FC-550 UGCC Random Polypropylene (CPP film grade)

### Application

Heat sealant layer for CPP film

Physical Properties*			
Physical	Testing methods	Nominal values	
Density (by Gradient technique)	ASTM D 1505	gr/cm <sup>3</sup>	0.85-0.95
Melt Flow Rate	ASTM D 1238	g/10min	7.0-9.0
<b>Mechanical</b>			
Tensile Strength at Yield, min.	ASTM D 638	kg f/cm <sup>2</sup>	260
Elongation at Break, min.	ASTM D 638	%	100
Flexural Modulus, min.	ASTM D 790	kg f/cm <sup>2</sup>	10000
<b>Impact</b>			
Notched Izod Impact Strength (23 °C), min.	ASTM D 256	kg f cm/cm	4
Notched Izod Impact Strength (-10 °C), min.	ASTM D 256	kg f cm/cm	-
<b>Thermal</b>			
Heat Deflection Temperature (4.6 kgf/cm <sup>2</sup> ), min.	ASTM D 648	°C	80
Vicat Softening Point	ASTM D 1525	°C	130
Melting Temperature	ASTM D 3418	°C	148

August, 2016

Note: Above data are based on information provided by Licensor and it is not to be construed as specifications, the latest exact data can be obtained from Uz-Kor Gas Chemical Central Plant Laboratory

# POLYMER SM

ООО «Полимер СМ»  
 117463, РФ, Москва, Новоясеневский пр., 32/1, офис 78  
 Тел.: +7 495 227 99 00      Моб.: +7 911 763 83 83  
 www.polymer-sm.com      polymersm@mail.ru