

J-170T UGCC Homo Polypropylene (Injection grade)

Application

Housewares, general supplies, transparent stationary, disposable syringes

Physical Properties*			
Physical	Testing methods	Nominal values	
Density (by Gradient technique)	ASTM D 1505	gr/cm ³	0.85-0.95
Melt Flow Rate	ASTM D 1238	g/10min	23-33
Mechanical			
Tensile Strength at Yield, min.	ASTM D 638	kg f/cm ²	350
Elongation at Break, min.	ASTM D 638	%	10
Flexural Modulus, min.	ASTM D 790	kg f/cm ²	17000
Impact			
Izod Impact Strength (23 °C), min.	ASTM D 256	kg f cm/cm	2
Izod Impact Strength (-10 °C), min.	ASTM D 256	kg f cm/cm	-
Thermal			
Heat Distortion Temperature (4.6 kgf/cm ²), min.	ASTM D 648	°C	105
Other properties			
Haze, max.	ASTM D 1003	%	40

August, 2016

Note: Above data are based on information provided by Licensor and it is not to be construed as specifications, the latest exact data can be obtained from Uz-Kor Gas Chemical Central Plant Laboratory

POLYMER SM

ООО «Полимер СМ»
 117463, РФ, Москва, Новоясеневский пр., 32/1, офис 78
 Тел.: +7 495 227 99 00 Моб.: +7 911 763 83 83
 www.polymer-sm.com polymersm@mail.ru