

JM-370 UGCC Block Polypropylene (Injection grade)

Application

Big size injection molding products, electric home appliances

Physical Properties*			
Physical	Testing methods	Nominal values	
Density (by Gradient technique)	ASTM D 1505	gr/cm ³	0.85-0.95
Melt Flow Rate	ASTM D 1238	g/10min	30-40
Mechanical			
Tensile Strength at Yield, min.	ASTM D 638	kg f/cm ²	240
Elongation at Break, min.	ASTM D 638	%	50
Flexural Modulus, min.	ASTM D 790	kg f/cm ²	11000
Impact			
Izod Impact Strength (23 °C), min.	ASTM D 256	kg f cm/cm	6
Izod Impact Strength (-10 °C), min.	ASTM D 256	kg f cm/cm	3
Thermal			
Heat Distortion Temperature (4.6 kgf/cm ²), min.	ASTM D 648	°C	90

August, 2016

Note: Above data are based on information provided by Licensor and it is not to be construed as specifications, the latest exact data can be obtained from Uz-Kor Gas Chemical Central Plant Laboratory

POLYMER SM

ООО «Полимер СМ»

117463, РФ, Москва, Новоясеневский пр., 32/1, офис 78

Тел.: +7 495 227 99 00

Моб.: +7 911 763 83 83

www.polymer-sm.com

polymersm@mail.ru