



L-270A UGCC Homo Polypropylene (Extrusion grade)

Application

Woven cloth, kraft paper coating

Physical Properties*			
Physical	Testing methods	Nominal values	
Density (by Gradient technique)	ASTM D 1505	gr/cm ³	0.85-0.95
Melt Flow Rate	ASTM D 1238	g/10min	24-28
Mechanical			
Tensile Strength at Yield, min.	ASTM D 638	kg f/cm ²	270
Elongation at Break, min.	ASTM D 638	%	100
Flexural Modulus, min.	ASTM D 790	kg f/cm ²	13000
Impact			
Izod Impact Strength (23 °C), min.	ASTM D 256	kg f cm/cm	2
Izod Impact Strength (-10 °C), min.	ASTM D 256	kg f cm/cm	-
Thermal			
Heat Distortion Temperature (4.6 kgf/cm ²), min.	ASTM D 648	°C	90
Vicat softening point, min.	ASTM D 1525	°C	140
Melting temperature	ASTM D 3418	°C	160

August, 2016

Note: Above data are based on information provided by Licensor and it is not to be construed as specifications, the latest exact data can be obtained from Uz-Kor Gas Chemical Central Plant Laboratory

POLYMER SM

ООО «Полимер СМ»

117463, РФ, Москва, Новоясеневский пр., 32/1, офис 78

Тел.: +7 495 227 99 00

Моб.: +7 911 763 83 83

www.polymer-sm.com

polymersm@mail.ru